

Ultra High Molecular Weight Polyethylene UTEC3041

Description:

UTEC3041 is an Ultra High Molecular Weight Polyethylene with a molecular weight greater than 10 times higher than High Density Polyethylene (HDPE) resins. This extremely high molecular weight yields several unique properties to this polymer such as high abrasion resistance, impact strength and because it is a self-lubricating material, a low coefficient of friction.

Applications:

Technical and porous parts, filters, compression molded sheets, Applications which require highest wear resistance and the use of pigments and/or additives

Physical Properties

Characteristics	Method	Units	Values
Intrinsic Viscosity	ASTM D 4020	dL/g	14
Average Molecular Weight	Internal	g/mol	3.0×10^6
Density	ASTM D 792	g/cm ³	0.925
Bulk Density	ASTM D 1895	g/cm ³	0.45
Average Particle Size Dp50	Laser Light Scattering	µm	160
Melt Temperature	ASTM D3418	°C	133

Mechanical Properties

Characteristics	Method	Units	Values
Tensile Strength at Yield	ASTM D 638 ISO 527	MPa	≥ 17
Tensile Strength at Break	ASTM D 638 ISO 527	MPa	> 30
Ultimate Elongation	ASTM D 638 ISO 527	%	> 350
Double Notch Charpy Impact Strength	ISO 11542-2	KJ/m ²	> 180
Shore D Hardness (15 sec)	ASTM D 2240 ISO 868	-	> 58

* Determined with double-notched specimens (14° v-notch on both sides) in accordance with ISO 11542-2.

Electrical Properties

Characteristics	Method	Units	Values
Volume Resistivity	ASTM D 257	ohm.cm	> 10 ¹⁴
Surface Resistivity	ASTM D 257	ohm	> 10 ¹²

Final Remarks

- It is the sole responsibility of the Client/Purchaser of this Product to verify the suitability of this Product and its use for the intended use and to ensure compliance with legal and regulatory requirements applicable to the final product.
- The technical guidance eventually rendered to the Client/Purchaser of the Product by Braskem about the Product does not characterize a performance guarantee for the intended application, nor does it exempt the Client/Purchaser from the responsibilities described in item 1 above.
- Any application information about the Product does not mean that Braskem knows or has validated the productive process of the Client/Purchaser or the adequacy of the Product for the intended application. All warranties of merchantability or fitness for a particular purpose, express or implied, are expressly excluded.
- The information provided herein is of the date hereof and Braskem may update, revise or amend the information contained herein at any time and without previous notice. The Client/Purchaser shall consult www.braskem.com to verify any updates to this information.
- For regulatory information associated with the Product and its source, please consult the Regulatory Information Sheet (RIS). For other requests, please contact Braskem's Technical Services area.
- The information contained herein is provided based on the best of Braskem's knowledge, indicating typical values of the properties of the Product, and such values shall not be considered absolute or as a guarantee.